

SAR Tissue Ingredients

Body Tissue Simulating Liquids			
Body Tissue (Muscle)	Parameters according to FCC KDB 865664 D01		
Narrow – Band Solutions ($\pm 5\%$ tolerance)	Product	Test Frequency [MHz]	Main Ingredients
	MSL750V2	750	Water, Sugar
	MSL900V2	835, 900	Water, Sugar
	MSL1800V2	1750, 1800	Water, DGBE
	MSL1950V2	1900, 2000	Water, DGBE
	MSL2450V2	2450	Water, DGBE
Broad – Band Solutions ($\pm 5\%$ tolerance)	Product	Test Frequency [MHz]	Main Ingredients
	MBBL3500–5800V5	3500–5800	Water, Oil

MSL750

The Item is composed of the following ingredients:

H ₂ O	Water, 35 – 58%
Sucrose	Sugar, white, refined, 40 – 60%
NaCl	Sodium Chloride, 0 – 6%
Hydroxyethyl-cellulose	Medium Viscosity (CAS# 9004-62-0), <0.3%
Preventol-D7	Preservative: aqueous preparation, (CAS# 55965-84-9), containing 5-chloro-2-methyl-3(2H)-isothiazolone and 2-methyl-3(2H)-isothiazolone, 0.1 – 0.7%
	Relevant for safety; Refer to the respective Safety Data Sheet*.

Schmid & Partner Engineering AG

s p e a g

Zeughausstrasse 43, 8004 Zurich, Switzerland
Phone +41 44 245 9700, Fax +41 44 245 9779
info@speag.com, http://www.speag.com

Measurement Certificate / Material Test

Item Name	Body Tissue Simulating Liquid (MSL 750)
Product No.	SL AAM 075 AA (Charge: 111107-3)
Manufacturer	SPEAG

Measurement Method

TSL dielectric parameters measured using calibrated OCP probe (type DAK).

Target Parameters

Target parameters as defined in the IEEE 1528 and IEC 62209 compliance standards.

Test Condition



Ambient Condition 22°C ; 30% humidity
TSL Temperature 22°C
Test Date 9-Nov-11

Additional Information

TSL Density 1.212 g/cm³
TSL Heat-capacity 3.006 kJ/(kg*K)

Results

f [MHz]	Measured		Target		Diff.to Target [%]	
	HP-e'	HP-e''	sigma	eps	sigma	Delta-eps
600	67.5	24.52	0.82	56.1	0.95	2.4 -14.0
625	57.2	24.24	0.84	56.0	0.95	2.0 -11.7
650	56.8	23.96	0.87	55.9	0.96	1.6 -9.3
675	56.6	23.68	0.89	55.8	0.96	1.3 -7.2
700	56.3	23.41	0.91	55.7	0.96	1.0 -6.0
725	56.0	23.17	0.93	55.6	0.96	0.7 -2.8
750	55.8	22.93	0.96	55.5	0.96	0.4 -0.7
775	55.5	22.75	0.98	55.4	0.97	0.1 1.6
800	55.2	22.58	1.01	55.3	0.97	-0.2 3.9
825	55.0	22.43	1.03	55.2	0.98	-0.5 5.2
838	54.8	22.35	1.04	55.2	0.98	-0.6 5.9
850	54.7	22.27	1.05	55.2	0.99	-0.8 6.5
875	54.5	22.12	1.08	55.1	1.02	-1.0 5.6
900	54.3	21.97	1.10	55.0	1.05	-1.3 4.7
925	54.0	21.84	1.12	55.0	1.06	-1.7 5.7
950	53.8	21.72	1.15	54.9	1.08	-2.1 6.7
975	53.6	21.63	1.17	54.9	1.09	-2.4 7.9
1000	53.4	21.53	1.20	54.8	1.10	-2.7 9.1



MSL900V2

The Item is composed of the following ingredients:

H ₂ O	Water, 35 – 58%
Sucrose	Sugar, white, refined, 40 – 60%
NaCl	Sodium Chloride, 0 – 6%
Hydroxyethyl-cellulose	Medium Viscosity (CAS# 9004-62-0), <0.3%
Preventol-D7	Preservative: aqueous preparation, (CAS# 55965-84-9), containing 5-chloro-2-methyl-3(2H)-isothiazolone and 2-methyl-3(2H)-isothiazolone, 0.1 – 0.7%
	Relevant for safety; Refer to the respective Safety Data Sheet*.

Schmid & Partner Engineering AG

s p e a g

Zeughausstrasse 43, 8004 Zurich, Switzerland
Phone +41 44 245 9700, Fax +41 44 245 9779
info@speag.com, http://www.speag.com

Measurement Certificate / Material Test

Item Name	Body Tissue Simulating Liquid (MSL900V2)
Product No.	SL AAM 090 CA (Charge: 130313-2)
Manufacturer	SPEAG

Measurement Method

TSL dielectric parameters measured using calibrated OCP probe.

Setup Validation

Validation results were within $\pm 2.5\%$ towards the target values of Methanol.

Target Parameters

Target parameters as defined in the IEEE 1528 and IEC 62209 compliance standards.


Test Condition

Ambient	Environment temperatur (22 \pm 3)°C and humidity < 70%.
TSL Temperature	22°C
Test Date	13-Mar-13
Operator	IEN

Additional Information

TSL Density	1.294 g/cm ³
TSL Heat-capacity	3.003 kJ/(kg*K)

f [MHz]	Measured		Target		Diff.to Target [%]		
	HP-e'	HP-e"	sigma	eps	sigma	Δ-eps	Δ-sigma
700	56.4	22.03	0.86	55.7	0.96	1.3	-10.6
725	56.2	21.87	0.88	55.6	0.96	1.0	-8.3
750	55.9	21.71	0.91	55.5	0.96	0.7	-6.0
775	55.7	21.58	0.93	55.4	0.97	0.4	-3.6
800	55.4	21.45	0.95	55.3	0.97	0.1	-1.3
825	55.1	21.33	0.98	55.2	0.98	-0.2	0.1
838	55.0	21.27	0.99	55.2	0.98	-0.3	0.8
850	54.9	21.21	1.00	55.2	0.99	-0.5	1.5
875	54.7	21.13	1.03	55.1	1.02	-0.7	0.9
900	54.4	21.04	1.05	55.0	1.06	-1.0	0.3
925	54.2	20.96	1.08	55.0	1.06	-1.4	1.5
950	54.0	20.88	1.10	54.9	1.08	-1.7	2.6
975	53.8	20.83	1.13	54.9	1.09	-2.0	4.0
1000	53.6	20.78	1.16	54.8	1.10	-2.3	5.3
1025	53.3	20.74	1.18	54.8	1.11	-2.7	6.6
1050	53.1	20.69	1.21	54.7	1.12	-3.0	7.9
1075	52.9	20.64	1.23	54.7	1.13	-3.3	9.1
1100	52.7	20.59	1.26	54.7	1.14	-3.6	10.2
1125	52.5	20.58	1.29	54.6	1.15	-3.9	11.6
1150	52.3	20.57	1.32	54.6	1.17	-4.2	12.9
1175	52.0	20.53	1.34	54.5	1.18	-4.5	14.0
1200	51.8	20.48	1.37	54.5	1.19	-4.8	15.1



MSL1800V2

The Item is composed of the following ingredients:

H2O Water, 52 – 75%
 C8H18O3 Diethylene glycol monobutyl ether (DGBE), 25 – 48%
 (CAS-No. 112-34-5, EC-No. 203-961-6, EC-index-No. 603-096-00-8)
 Relevant for safety; Refer to the respective Safety Data Sheet*.
 NaCl Sodium Chloride, <1.0%

f (MHz)	HP-e'	HP-e"	sigma	P/N: SL AAM 180 CA		TARGET PARAMETERS		
				Charge: 061204_1-3	Mea Date: 20-Dez-06	f (MHz)	eps	sigma
300	58.68	20.34	0.34			1800	53.3	1.52
350	58.52	18.25	0.36			1900	53.3	1.52
400	58.28	16.80	0.37					
450	58.17	15.77	0.39					
500	57.98	14.94	0.42					
550	57.81	14.35	0.44					
600	57.62	13.92	0.46					
650	57.46	13.59	0.49					
700	57.28	13.33	0.52					
750	57.09	13.18	0.55					
800	56.91	13.04	0.58					
850	56.66	12.88	0.61					
900	56.86	12.68	0.63					
950	56.65	13.03	0.69					
1000	56.42	13.06	0.73					
1050	56.20	13.18	0.77					
1100	55.94	13.22	0.81					
1150	55.73	13.28	0.85					
1200	55.50	13.30	0.89					
1250	55.45	13.30	0.92					
1300	55.33	13.57	0.98					
1350	55.08	13.75	1.03					
1400	54.74	13.86	1.08					
1450	54.51	13.87	1.12					
1500	54.38	13.90	1.16					
1550	54.26	14.07	1.21					
1600	53.99	14.20	1.26					
1650	53.84	14.27	1.31					
1700	53.66	14.37	1.36					
1750	53.54	14.44	1.41					
1800	53.48	14.62	1.46					
1850	53.34	14.84	1.53					
1900	53.16	15.05	1.59					
1950	52.96	15.29	1.66					
2000	52.68	15.49	1.72					
2050	52.35	15.59	1.78					
2100	52.10	15.62	1.83					
2150	51.91	15.55	1.86					
2200	51.97	15.59	1.91					
2250	51.97	15.82	1.98					
2300	51.86	16.17	2.07					
2350	51.57	16.45	2.15					
2400	51.29	16.63	2.22					
2450	51.02	16.79	2.29					
2500	50.80	16.91	2.35					
2550	50.57	17.03	2.42					
2600	50.36	17.15	2.48					
2650	50.17	17.26	2.54					
2700	49.99	17.39	2.61					
2750	49.82	17.53	2.68					
2800	49.61	17.71	2.76					
2850	49.39	17.88	2.83					
2900	49.12	18.02	2.91					
2950	48.87	18.19	2.98					
3000	48.62	18.22	3.04					

Difference to Target (%)

f (MHz)	Δ-eps	Δ-sigma
1800	0.3	-3.7
1900	-0.3	4.7

MSL1950V2

The Item is composed of the following ingredients:

H2O Water, 52 – 75%
 C8H18O3 Diethylene glycol monobutyl ether (DGBE), 25 – 48%
 (CAS-No. 112-34-5, EC-No. 203-961-6, EC-index-No. 603-096-00-8)
 Relevant for safety; Refer to the respective Safety Data Sheet*.
 NaCl Sodium Chloride, <1.0%

f (MHz)	HP- ϵ'	HP- ϵ''	sigma	P/N:	TARGET PARAMETERS		
Charge:	SL AAM 195 BA			Mea Date:	f (MHz)	eps	sigma
300	58.26	12.08	0.20	061211_1-3	1950	53.3	1.52
350	58.05	11.15	0.22	Mea Date: 20-Dec-06	2000	53.3	1.52
400	57.96	10.54	0.23	Temp (°C)	22		
450	57.85	10.15	0.25				
500	57.67	9.87	0.27				
550	57.56	9.72	0.30				
600	57.37	9.65	0.32				
650	57.27	9.65	0.35				
700	57.12	9.68	0.38				
750	56.95	9.75	0.41				
800	56.77	9.83	0.44				
850	56.56	9.87	0.47				
900	56.75	9.80	0.49				
950	56.58	10.31	0.54				
1000	56.36	10.51	0.58				
1050	56.16	10.77	0.63				
1100	55.86	10.94	0.67				
1150	55.64	11.10	0.71				
1200	55.40	11.19	0.75				
1250	55.34	11.26	0.78				
1300	55.24	11.60	0.84				
1350	54.96	11.85	0.89				
1400	54.66	12.03	0.94				
1450	54.42	12.10	0.98				
1500	54.34	12.19	1.02				
1550	54.19	12.44	1.07				
1600	53.96	12.62	1.12				
1650	53.79	12.75	1.17				
1700	53.63	12.89	1.22				
1750	53.49	13.03	1.27				
1800	53.44	13.23	1.33				
1850	53.31	13.52	1.39				
1900	53.10	13.78	1.46				
1950	52.92	14.07	1.53				
2000	52.61	14.31	1.59				
2050	52.27	14.45	1.65				
2100	51.98	14.52	1.70				
2150	51.79	14.47	1.73				
2200	51.83	14.53	1.78				
2250	51.82	14.78	1.85				
2300	51.69	15.14	1.94				
2350	51.41	15.44	2.02				
2400	51.12	15.64	2.09				
2450	50.88	15.82	2.16				
2500	50.62	15.96	2.22				
2550	50.42	16.10	2.28				
2600	50.17	16.25	2.35				
2650	50.00	16.36	2.41				
2700	49.81	16.52	2.48				
2750	49.65	16.65	2.55				
2800	49.44	16.87	2.63				
2850	49.20	17.03	2.70				
2900	48.95	17.23	2.78				
2950	48.67	17.38	2.85				
3000	48.44	17.46	2.91				

f (MHz)	ϵ'	conductivity
1900	53.10	1.46
1950	52.92	1.53
2000	52.61	1.59

f (MHz)	Difference to Target (%)	
	Δ -eps	Δ -sigma
1950	-0.7	0.4
2000	-1.3	4.8

MSL2450V2

The Item is composed of the following ingredients:

H2O Water, 52 – 75%
C8H18O3 Diethylene glycol monobutyl ether (DGBE), 25 – 48%
(CAS-No. 112-34-5, EC-No. 203-961-6, EC-index-No. 603-096-00-8)
NaCl Relevant for safety; Refer to the respective Safety Data Sheet*.
Sodium Chloride, <1.0%

Schmid & Partner Engineering AG

s p e a g

Zeughausstrasse 43, 8004 Zurich, Switzerland
Phone +41 44 245 9700, Fax +41 44 245 9779
info@speag.com, http://www.speag.com

Measurement Certificate / Material Test

Item Name	Body Tissue Simulating Liquid (MSL2450V2)
Product No.	SL AAM 245 BA (Charge: 130502-1)
Manufacturer	SPEAG

Measurement Method

TSL dielectric parameters measured using calibrated OCP probe.

Setup Validation

Validation results were within $\pm 2.5\%$ towards the target values of Methanol.

Target Parameters

Target parameters as defined in the IEEE 1528 and IEC 62209 compliance standards.



Test Condition

Ambient	Environment temperatur (22 ± 3)°C and humidity < 70%.
TSL Temperature	22°C
Test Date	2-May-13
Operator	IEN

Additional Information

TSL Density	0.996 g/cm ³
TSL Heat-capacity	3.987 kJ/(kg*K)

I [MHz]	Measured	Target	Diff. to Target	[%]
	HP-e ⁺	HP-e ⁺ sigma	eps	sigma
1900	52.5	12.14	1.28	53.3 1.52
1925	52.4	12.25	1.31	53.3 1.52
1950	52.3	12.35	1.34	53.3 1.52
1975	52.2	12.47	1.37	53.3 1.52
2000	52.1	12.59	1.40	53.3 1.52
2025	52.0	12.70	1.43	53.3 1.54
2050	52.0	12.82	1.46	53.2 1.57
2075	51.9	12.93	1.49	53.2 1.58
2100	51.8	13.03	1.52	53.2 1.62
2125	51.7	13.14	1.55	53.1 1.64
2150	51.6	13.25	1.58	53.1 1.66
2175	51.5	13.36	1.62	53.1 1.69
2200	51.4	13.46	1.65	53.0 1.71
2225	51.3	13.57	1.68	53.0 1.74
2250	51.2	13.67	1.71	53.0 1.76
2275	51.1	13.78	1.74	52.9 1.78
2300	51.0	13.89	1.78	52.9 1.81
2325	51.0	14.00	1.81	52.9 1.83
2350	50.8	14.11	1.84	52.8 1.85
2375	50.8	14.21	1.88	52.8 1.88
2400	50.7	14.32	1.91	52.8 1.90
2425	50.6	14.43	1.95	52.7 1.93
2450	50.5	14.53	1.98	52.7 1.95
2475	50.4	14.63	2.02	52.7 1.99
2500	50.3	14.73	2.06	52.6 2.02
2525	50.2	14.85	2.09	52.6 2.06
2550	50.1	14.96	2.12	52.6 2.09
2575	50.0	15.05	2.16	52.5 2.13
2600	49.9	15.13	2.19	52.5 2.16
2625	49.8	15.23	2.22	52.5 2.20
2650	49.7	15.33	2.26	52.4 2.23
2675	49.6	15.43	2.30	52.4 2.27
2700	49.5	15.52	2.33	52.4 2.30



MBBL3500-5800V5

The Item is composed of the following ingredients:

Water 60 – 80%

Esters, Emulsifiers, Inhibitors 20 – 40%

Sodium salt 0 – 1.5%

Safety relevant ingredients according to Swiss and EU directives: none

Safety relevant ingredients according to other directives:

CAS 26399-02-0 10 – 28% Oleic acid, alkylester

Schmid & Partner Engineering AG

s p e a g

Zeughausstrasse 43, 8004 Zurich, Switzerland
Phone +41 44 245 9700, Fax +41 44 245 9779
info@speag.com, http://www.speag.com

Measurement Certificate / Material Test

Item Name	Body Tissue Simulating Liquid (MBBL3500-5800V5)				
Product No.	SL AAM 501 EA (Charge: 130528-2)				
Manufacturer	SPEAG				

Measurement Method

TSL dielectric parameters measured using calibrated OCP probe.

Setup Validation

Validation results were within $\pm 2.5\%$ towards the target values of Methanol.

Target Parameters

Target parameters as defined in the IEEE 1528 and IEC 62209 compliance standards.

Test Condition

Ambient	Environment temperatur (22 \pm 3) $^{\circ}$ C and humidity < 70%.
TSL Temperature	22°C
Test Date	29-May-13
Operator	IEN

Additional Information

TSL Density

TSL Heat-capacity

f [MHz]	Measured		Target	Diff.to Target [%]	
	HP-e ⁺	HP-e ⁻		sigma	Delta-eps
3400	51.9	16.39	3.10	51.5	3.20
3500	51.8	16.43	3.20	51.3	3.31
3600	51.7	16.52	3.31	51.2	3.43
3700	51.5	16.60	3.42	51.1	3.55
3800	51.4	16.65	3.52	50.9	3.66
3900	51.3	16.72	3.63	50.8	3.78
4000	51.2	16.83	3.74	50.8	3.90
4100	51.0	16.91	3.86	50.5	4.01
4200	50.9	17.04	3.98	50.4	4.13
4300	50.8	17.23	4.12	50.2	4.25
4400	50.6	17.40	4.26	50.1	4.37
4500	50.4	17.51	4.38	50.0	4.48
4600	50.2	17.63	4.51	49.8	4.60
4700	50.0	17.72	4.63	49.7	4.72
4800	49.9	17.81	4.75	49.6	4.83
4850	49.8	18.00	4.86	49.5	4.89
4900	49.8	17.96	4.90	49.4	4.95
4950	49.6	18.07	4.98	49.4	5.01
5000	49.7	18.14	5.05	49.3	5.07
5050	49.5	18.13	5.09	49.2	5.12
5100	49.4	18.26	5.18	49.2	5.18
5150	49.3	18.26	5.23	49.1	5.24
5200	49.2	18.38	5.32	49.0	5.30
5250	49.1	18.38	5.37	48.9	5.36
5300	49.0	18.50	5.45	48.9	5.42
5350	49.0	18.52	5.51	48.8	5.47
5400	48.8	18.58	5.58	48.7	5.53
5450	48.8	18.66	5.66	48.7	5.59
5500	48.7	18.64	5.70	48.6	5.65
5550	48.6	18.76	5.79	48.5	5.71
5600	48.6	18.76	5.85	48.5	5.77
5650	48.4	18.87	5.93	48.4	5.82
5700	48.4	18.89	5.99	48.3	5.88
5750	48.3	18.99	6.08	48.3	5.94
5800	48.2	19.01	6.13	48.2	6.00
5850	48.1	19.10	6.22	48.1	6.06
5900	48.1	19.16	6.29	48.1	6.12

