

Desktop/ISO14443-4/e-Doc

FCC-ID: P4E-SMARTPIN-3

P/N: 800-8250 V2.0

S/N: 0602-0005 **CE**

Conf: 01SMR-4110



Desktop/ISO14443-4/e-Doc
FCC-ID: P4E-SMARTPIN-3
P/N: 800-8250 V2.0
S/N: 0602-0005 CE
Conf: 01SMR-4110



Providing Solutions in Pressure Sensitive Films

Product Construction Sheet

THERMLfilm® SELECT™ 22944E

GENERAL DESCRIPTION:

This is a top-coated thermal transfer printable silver matte polyester film coated with a permanent pressure sensitive acrylic adhesive and backed with a white glassine release liner.

UL/CSA RECOGNITION:

This is an UL recognized and CSA listed product. For further information, please reference FLEXcon's UL file No. MH16635 (N), CSA file No. 099214 L 000 or contact your FLEXcon Representative.

PRODUCT DATA	VALUE	TEST METHOD
PHYSICAL PROPERTIES		
Thickness (micron)	Film: 50 Adhesive: 20-23 Liner: 56	+/- 10 % +/- 3 +/- 10 %
		ASTM D 3652
Dimensional Stability (%)	No shrinkage observed	On Al panel at 70°C for 24 hr.

ADHESION PROPERTIES**

Adhesion from (N/m)	Average	
Stainless Steel	737	FTM 1 (Modified for 72 hr dwell time)
Acrylic	781	
Glass	759	
Polypropylene	528	
Expected Shear	50 +	FTM 8
Tack (gm/sq cm)	540	ASTM D 2979

** For guidance only

This data is based on limited test results due to the custom nature of this product, not to be used for setting specifications.

EXPECTED EXTERIOR LIFE	Two years
SERVICE TEMPERATURE RANGE	-40°C to 150°C
MINIMUM APPLICATION TEMPERATURE	10°C
STORAGE STABILITY	Two years stored at 21°C and 50% RH

* THERMLfilm is a registered trademark and SELECT is a trademark of FLEXcon Company, Inc. 06/01/2006

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.